

## **Expanded Polystyrene (EPS)**EIFS Insulation Board

## **PRODUCT DESCRIPTION**


**Expanded Polystyrene (EPS)** insulation board for DuROCK Exterior Insulation Finish Systems is made of 100% virgin polystyrene resin, aged and cut in accordance with the requirements of ASTM E2430, and compliant with ULC-S701. EPS insulation board is made by a DuROCK-approved manufacturer, and is packaged in bags with DuROCK's logo plainly visible. Please refer to EIF System specifications for applicable thicknesses and sheet size.

EPS insulation board is available in either flat or in the patented DuROCK **PUCCS** configuration. DuROCK **PUCCS** grooves are 10 mm ( $^{13}$ /<sub>32</sub> inch) deep by 16 mm ( $^{5}$ /<sub>8</sub> inch) wide in 51 mm (2 inch) radii, with seventy-two circles cut equidistantly on 102 mm (4 inches) vertical and horizontal centres, tangentially overlapping.

Refer to the applicable EIF System specifications and details for installation information.

## **PHYSICAL PROPERTIES**

CAN/ULC-S701	TYPE 1	TYPE 2
Min. Thermal Resistance (for 25 mm)	0.65 m <sup>2.0</sup> C/W	0.70 m <sup>2.0</sup> C/W
Min. Thermal Resistance (for 1 inch)	3.70 ft <sup>2.</sup> hr <sup>.o</sup> F/BTU	4.00 ft <sup>2.</sup> hr <sup>.</sup> °F/BTU
Max. Vapour Permeance (for 25 mm)	300 ng/Pa <sup>·</sup> s·m <sup>2</sup>	200 ng/Pa·s·m²
Max. Vapour Permeance (for 1 inch)	5.2 perms	3.5 perms
Max. Dimensional Stability	1.5%	1.5%
Min. Flexural Strength	170 kPa (25 psi)	240 kPa (35 psi)
Max. Water Absorption (by volume)	6%	4%
Min. Compressive Strength	70 kPa (10 psi)	110 kPa (16 psi)
Min. Limiting Oxygen Index	24%	24%
CAN/ULC-S102		
Flame Spread Rating	25-500 ৢ	25-500 ু
Average Density	16 kg/m³	24 kg/m <sup>3</sup>
	1.0 pcf	1.5 pcf



Refer to www.DuROCK.com for the most up-to-date version of this document.