

Spacco

Faux Finish Wall Coating

PRODUCT DESCRIPTION

DuROCK Spacco is a decorative protective coating designed for use as a textured free hand faux finish. **Spacco** is ideal for use in both interior and exterior applications, in new construction or renovations, and in commercial, industrial, institutional and residential projects. **Spacco** is a 100% acrylic, flexible, breathable coating. **Spacco** is a trowel-applied finish texture that can be custom coloured upon request.

STORAGE & MIXING

Store **Spacco** above 4°C (40°F) and below 40°C (104°F), off the ground and in a dry place away from direct sunlight. Under no circumstances shall **Spacco** be permitted to freeze.

Using a stainless steel or corrosion resistant mixing blade and power drill, mix at 400 – 500 rpm, ensuring not to induce air into the product. Mix product until a uniform consistency is attained. Up to 250mL (8oz) of potable water can be added to a full pail of **Spacco** to adjust workability in hot temperature conditions. Accelerators and other additives are prohibited.

APPLICATION & COVERAGE

Substrate must be clean, dry, and free of cracks or loose material. Surface and ambient temperatures must be at least 4°C (40°F) for a minimum of 24 hours, and must remain so until the **Spacco** has dried. Do not apply **Spacco** to a frozen base or a base containing frost. Wherever possible avoid application in direct sunlight. Protect material from excessive evaporation during dry weather.

Prior to application, prime area with **DuROCK Base Coat Primer**. Allow a minimum of 2hrs for prime coat to dry. Remix **Spacco** prior to use. With a stainless steel trowel apply a skim coat to the primed surface. Allow to dry approximately 2hrs. Again, using a stainless steel trowel apply a final coat using a skip trowel motion. This creates depth and texture in the surface. Allow the product to dry until the surface is almost tack free. At this point knock down the surface with a plastic float, keeping the plastic float clean by wiping it with a damp sponge. Allow 24hrs for the **Spacco** to dry. Once dry, surface can be glazed using **DuROCK Glaze**.

Using a slightly dampened sponge, dip the sponge into the glaze and work the glaze over the entire surface. Backwash the glaze using the same dampened sponge until the desired colour is achieved.

DuROCK Spacco is available in 19 L (4.18 gallons) pails (25 kg/pail) with an average coverage rate of 140ft² at a thickness of 3/16 in. This coverage is only an approximation as actual rates are dependent upon jobsite conditions and other factors.

TECHNICAL DATA

Available upon request

Refer to www.DuROCK.com for the most up-to-date version of this document.